



R.E.A.L. SEAL CO.
MATERIAL DATA SHEET
COMPOUND # 2673

<u>ORIGINAL PHYSICAL PROPERTIES</u>	<u>SPEC</u>	<u>2673</u>
HARDNESS, SHORE A PTS	80 +/- 5	81
ULTIMATE TENSILE STRENGTH, PSI	1450 MIN	3845
ULTIMATE ELONGATION, %	100 MIN	267
MODULUS @ 100%, PSI	-----	1377

HEAT RESISTANCE (ASTM D 573)

70 HRS @ 100 C

CHANGE IN HARDNESS, PTS	+15 MAX	+2
CHANGE IN TENSILE, %	-20 MAX	-7
CHANGE IN ELONGATION, %	-40 MAX	-15

OIL RESISTANCE (ASTM D 471)

70 HRS IN OIL #1 @ 100 C

CHANGE IN HARDNESS, PTS	-5 TO +15	+1
CHANGE IN TENSILE, %	-25 MAX	-2
CHANGE IN ELONGATION, %	-45 MAX	-4
CHANGE IN VOLUME, %	-10 TO +5	-2

OIL RESISTANCE (ASTM D 471)

70 HRS IN OIL #1 @ 121 C

CHANGE IN HARDNESS, PTS	-5 TO +15	-1
CHANGE IN TENSILE, %	-25 MAX	-3
CHANGE IN ELONGATION, %	-45 MAX	-14
CHANGE IN VOLUME, %	-10 TO +5	-2

OIL RESISTANCE (ASTM D 471)

70 HRS IN OIL #3 @ 100 C

CHANGE IN HARDNESS, PTS	0 TO -15	-7
CHANGE IN TENSILE, %	-45 MAX	-16
CHANGE IN ELONGATION, %	-45 MAX	-21
CHANGE IN VOLUME, %	0 TO +35	+19

COMPRESSION SET (ASTM D 395B)

22 HRS @ 100 C

% SET	50 MAX	16
-------	--------	----

LOW TEMPERATURE RETRACTION (ASTM D 1329)

TR-10, DEGREES C	REPORT	-24
------------------	--------	-----

INTERNAL LUBRICATION

REPORT

YES

CARBOXILATED

REPORT

YES

COLOR

REPORT

BLACK