



R.E.A.L. SEAL CO., INC.
1971 DON LEE PL.
ESCONDIDO CA 92029 USA
PHONE:(760) 743-7263 FAX: (760) 740-0852

R.E.A.L. SEAL CO.
MATERIAL DATA SHEET
COMPOUND # 3350

<u>ORIGINAL PHYSICAL PROPERTIES</u>	<u>SPEC</u>	<u>3350</u>
HARDNESS, SHORE A PTS	50 +/- 5	53
ULTIMATE TENSILE STRENGTH, PSI	1160 MIN	2470
ULTIMATE ELONGATION, %	350 MIN	410
MODULUS @ 100%, PSI	REPORT	220
<u>TEAR RESISTANCE (ASTM D 624 DIE C)</u>		
PLI	150 MIN	208
<u>COMPRESSION SET (ASTM D 395B)</u>		
<u>22 HRS @ 70 C</u>		
% SET	35 MAX	18
<u>COLOR</u>	REPORT	BLACK